



# Triple-S Chemical Products, Inc.

3464 Union Pacific Avenue  
Los Angeles, CA 90023  
[www.ssschemical.com](http://www.ssschemical.com)

Toll Free: (888) 417-5214  
Tel: (323) 261-7301  
Fax: (323) 261-5567

---

## AL - 70 QUICK DRY LACQUER

### DESCRIPTION:

**Triple-S' AL-70 Quick Dry Solvent Based Lacquer** is recommended for decorative purposes, abrasion resistance and intended for use by engineers and manufacturers of a wide variety of products. The exceptionally fast dry feature of **AL-70** makes an ideal coating for use in high production painting and decoration. It may be applied to metal, fiberglass or most rigid materials.

### APPLICATION:

It is designed primarily for conventional and airless spray application, but may be used in a dip system with careful control. Dipping is a good method of application if pieces are small enough to fit into a dip tank. If dipping, immersion time is 5 to 10 seconds and usually will dry in air within 15 to 30 minutes. Rolling is also an acceptable form of application. A 1/4 inch or 3/8 inch roller would be recommended. Brushing can leave streak lines and hence not a recommended application technique.

### ADVANTAGES:

- Easy to apply.
- Dries fast.
- Saves money by speeding up production.
- Strong adhesion.
- Clear sealer.

### PHYSICAL PROPERTIES:

Color:	Clear.
Finish:	Gloss or Flat
Solvent:	Aliphatic Hydrocarbons, xylene, toluene & Ketone
Flash Point:	23° F TCC
Dry to touch:	15 minutes
% solids by volume:	47-49
% solids by weight:	56-64
Coverage:	200-250 sq. ft. per gallon
Viscosity:	65-70 KREB Units @ 77° F
Recoat time:	Within 1 hour, or wait 24 hours
V.O.C.	Less than 250 grams per liter.

The information stated herein is based on information and tests we believe to be reliable. The accuracy or completeness thereof is not guaranteed. Since conditions of use are outside our control, user shall, before using, determine the suitability of the product for his intended use and user assumes all risk and liability whatsoever in connection therewith.